



EVS-1529

Semi-Conductive Silicone Compound

PRODUCT DESCRIPTION

EVS-1529 is a 65 durometer semi-conductive silicone compound. This product is supplied as fully cured, conductive sheet stock or ready-to-mold compound. The data below was generated using ASTM test method and procedures.

Technical Data	Typical Values
Shore A (60- 70 range)	65
Tensile psi (500 minimum)	1000 psi
Elongation % (150-300 range)	200%
Compression Set %	7.5%
Specific Gravity	1.17
Volume Resistivity ohm / cm (10 max)	7 ohm /cm
Color	Black
Thermal Stability Range	-60°C - 220°C

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.

CATALYZING

Store in a cool, dry environment.

SHELF LIFE

The shelf life of EVS1529 is 2 months. Cold storage may extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.



CR Technology, Inc

55 Chase St
Methuen, Massachusetts 01844

sales@crtechinc.com

978.681.5300