

PRODUCT DESCRIPTION

EVS416-65 is a 65 durometer silicone that is filled with silver plated glass beads. This product is supplied as fully cured, conductive sheet stock or ready-to-mold compound. The data below was generated using ASTM test method and procedures. EVS416-65 was designed to meet the requirements outlined in the MIL-G-83528C-Type M specifications.

Technical Data	Typical Values
Shore A (58- 72 range)	65
Tensile psi (200 minimum)	240 psi
Elongation % (100-300 range)	280%
Tear "B" ppi (30 min)	45
Specific Gravity (1.06 - 2.2)	1.8
Volume Resistivity ohm / cm (0.006 max)	.006 ohm /cm
Color	Tan or Gray
Thermal Stability Range	-60°C - 220°C

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.



CR Technology, Inc

55 Chase St
Methuen, Massachusetts 01844

sales@crtechinc.com

978.681.5300